

# General instructions for cleaning and care

## no.2 Rubber surfacing (smooth or with slight profile structure)
















**cleaning system without treatment  
end of construction**

object \_\_\_\_\_  
address \_\_\_\_\_  
room classification \_\_\_\_\_

date \_\_\_\_\_  
customer \_\_\_\_\_  
representative \_\_\_\_\_

work process: select one work stage from each number

| cleaning method  |   | * recommendations<br>chemical products | dosage                    | * recommendations<br>pad / brush / mop / cloth   | recommendations<br>machine / tool                             | comments   |
|--|---|--|---------------------------|--|---|--|
| 1  |  dry vacuum cleaning                 |  |                           | <b>Dust roller nozzle</b><br><b>Neverclog filter without ring</b><br><b>Filter bag with ring</b> | <b>Twinvac /</b><br>Duovac /<br>Silento /                     | large areas:<br>sweeping   |
| 2  |  dusting<br>damp mopping             |  |                           | <b>Masslinn 2000/Floorwit white</b>  | <b>Balit Varifix/</b><br>Balit/                               |  |
| cleaning without maintenance care product (if coating follows)   |   |  |                           |  |   |  |
| 3  |  wet mopping<br>direct method        | <b>Ecofloor</b><br>V Reshine           | <b>0.5 - 1%</b><br>3 - 5% | S <b>Micro-Mop Top/</b><br>Microsol mop/   | <b>Socar / Drewell</b>  |   |
| 3  |  scrubber drying<br>direct method    | <b>Ecofloor</b><br>V Reshine           | <b>0.5 - 1%</b><br>3 - 5% | ● <b>Pad red/</b><br>S ● Microsol fibre pad/<br>V ● Pad blue/                                    | <b>Duomatic / Laser</b><br>Mambo / Samba<br>Sprinter / iMatic |  |
| 3  |  wet scrubbing and<br>wet vacuuming | <b>Antiwax forte</b><br>Antiwax        | <b>2 - 5%</b><br>2 - 5%   | ● <b>Pad red/</b><br>S ● Microsol fibre pad/<br>V ● Pad blue/                                    | <b>Monomatic LS /</b><br><b>Watertank</b><br><b>Duovac /</b>  | heavily soiled   |
| cleaning with maintenance care (first protective treatment with same product as in maintenance cleaning) |   |  |                           |  |   |  |
| 4  |  wet mopping<br>direct method      | <b>Redur</b>                           | <b>3%</b>                 | S <b>Flat mop/</b><br>Microsol mop/  | <b>Socar / Drewell</b>  |   |
| 4  |  scrubber drying<br>direct method  | <b>Redur</b>                           | <b>3%</b>                 | ● <b>Pad red/</b><br>S ● Microsol fibre pad/   | <b>Duomatic / Laser</b><br>Mambo / Samba<br>Sprinter / iMatic |  |
| 4  |  spray cleaning<br>full spray      | <b>Polyspray</b>                       | <b>100%</b>               | ● <b>Pad red/</b><br>P ● Pad yellow/   | <b>Monomatic DS /</b><br><b>Spray unit</b>                    | after polishing   |

\* basic treatment / structure: B: coated / C: waxed / D: oiled / E: sealed / F: untreated / G: maintenance care product / P: polishing / S: structured / V: heavily soiled

**important:** When spray cleaning, you should change your pad often

# General instructions for cleaning and care

## no.2 Rubber surfacing (smooth or with slight profile structure)



### maintenance cleaning

object \_\_\_\_\_

date \_\_\_\_\_






























address \_\_\_\_\_

customer \_\_\_\_\_

room classification \_\_\_\_\_

representative \_\_\_\_\_

work process: select one work stage from each number

| ↓                            | cleaning method   |                                  | frequency   | recommendations<br>chemical products  | dosage                                | recommendations<br>pad / brush / mop / cloth  | recommendations<br>machine / tool                               | comments  |
|------------------------------|---|----------------------------------|---|---------------------------------------|---------------------------------------|---|---|---|
|                              |   |                                  |   | *                                     |                                       | *   |   |   |
| 1                            |    | dusting<br>damp mopping          |    |                                       |                                       | S <b>Masslinn 2000/Floorwit white</b><br>Synthetic fur  | <b>Balit Varifix/</b><br>Balit/                                 |   |
| 2                            |    | chewing gum<br>removal           |    | <b>Karpfrost</b><br>Karpotek          | <b>100%</b>                           |   |   | if needed          |
| cleaning without maintenance |   |                                  |   |                                       |                                       |   |   |   |
| 3                            |    | wet mopping<br>direct method     |    | <b>Ecofloor</b><br>Reshine<br>Alcosal | <b>0.5 - 1%</b><br>1 - 2%<br>1 - 2%   | S <b>Mop Variwet</b><br>Mop Microbrush/<br>V Micro-Mop Top/   | <b>Variwet / B. Varifix</b><br>Wetbox system<br>Socar / Drewell |                    |
| 3                            |    | scrubber drying<br>direct method |    | <b>Ecofloor</b><br>Libero<br>Reshine  | <b>0.5 - 1%</b><br>0.5 - 3%<br>1 - 2% | S  <b>Pad red/</b><br> Microsol fibre pad/        | <b>Duomatic / Laser</b><br>Mambo / Samba<br>Sprinter / iMatic   |   |
| 3                            |    | polishing, vacuum<br>polishing   |    |                                       |                                       | B  <b>Pad Blue Ice/</b><br>B  Microsol fibre pad/ | <b>Monomatic HS /</b><br><b>Suction ring Monon</b>              | after polishing    |
| cleaning with maintenance    |   |                                  |   |                                       |                                       |   |   |   |
| 3                            |  | wet mopping<br>direct method     |  | <b>Redur</b>                          | <b>1%</b>                             | S <b>Mop Variwet</b><br>Mop Microbrush/   | <b>Socar / Drewell</b><br>Wetbox system<br>Variwet / B. Varifix |                  |
| 3                            |  | scrubber drying<br>direct method |  | <b>Redur</b>                          | <b>1%</b>                             | S  <b>Pad red/</b><br> Microsol fibre pad/    | <b>Duomatic / Laser</b><br>Mambo / Samba<br>Sprinter / iMatic   |   |
| 3                            |  | spray cleaning<br>partial spray  |  | <b>Polyspray</b>                      | <b>100%</b>                           | P  <b>Pad red/</b><br> Pad yellow/            | <b>Monomatic DS /</b><br><b>Spray unit</b>                      | after polishing  |

\* basic treatment / structure: B: coated / C: waxed / D: oiled / E: sealed / F: untreated / G: maintenance care product / P: polishing / S: structured / V: heavily soiled

**important:** When spray cleaning, you should change your pad often

# General instructions for cleaning and care

## no.2 Rubber surfacing (smooth or with slight profile structure)



### interim cleaning

object \_\_\_\_\_

date \_\_\_\_\_






















address \_\_\_\_\_

customer \_\_\_\_\_

work process: select one work stage from each number

room classification \_\_\_\_\_

representative \_\_\_\_\_

|                                     | cleaning method  | frequency                | * recommendations chemical products       | dosage                     | * recommendations pad / brush / mop / cloth   | recommendations machine / tool                                | comments  |
|-------------------------------------|--|--------------------------|---|----------------------------|---|---|---|
| 1                                   |  dusting<br>damp mopping            | <input type="checkbox"/> |   |                            | S <b>Masslinn 2000/Floorwit white</b><br>Synthetic fur  | <b>Balit Varifix/</b><br>Balit/                               |   |
| 1                                   |  dry vacuum cleaning                | <input type="checkbox"/> |   |                            | V <b>Dust roller nozzle</b>   | <b>Monovac /</b><br>Scuba                                     |   |
| 2                                   |  chewing gum removal                | <input type="checkbox"/> | <b>Karpfrost</b><br>Karpotek              | 100%                       |   |   | if needed    |
| <b>cleaning without maintenance</b> |  |                          |   |                            |   |   |   |
| 3                                   |  wet mopping<br>indirect method     | <input type="checkbox"/> | <b>Polex</b><br>B Reshine<br>G Rewit 2000 | 2 - 4%<br>3 - 5%<br>2 - 5% | <b>Mop Microbrush/</b><br>Micro-Mop Top/  | <b>Wetbox system</b><br>Socar / Drewell                       |   |
| 3                                   |  scrubber drying<br>indirect method | <input type="checkbox"/> | <b>Polex</b><br>B Reshine<br>G Rewit 2000 | 2 - 4%<br>3 - 5%<br>2 - 5% |  <b>Pad red/</b><br>S  <b>Microsol fibre pad/</b><br>V  <b>Pad blue/</b> | <b>Duomatic / Laser</b><br>Mambo / Samba<br>Sprinter / iMatic |   |
| 3                                   |  polishing, vacuum<br>polishing    | <input type="checkbox"/> |   |                            | B  <b>Pad Blue Ice/</b><br>B  <b>Microsol fibre pad/</b>   | <b>Monomatic HS /</b><br><b>Suction ring Monon</b>            | after polishing   |
| <b>cleaning with maintenance</b>    |  |                          |   |                            |   |   |   |
| 3                                   |  spray cleaning<br>full spray     | <input type="checkbox"/> | <b>Polyspray</b>                          | 100%                       |  <b>Pad red/</b><br>P  <b>Pad yellow/</b>   | <b>Monomatic DS /</b><br><b>Spray unit</b>                    | after polishing    |

\* basic treatment / structure: B: coated / C: waxed / D: oiled / E: sealed / F: untreated / G: maintenance care product / P: polishing / S: structured / V: heavily soiled

**important:** When spray cleaning, you should change your pad often  
For initial cleaning after interim cleaning, see "initial cleaning".

# General instructions for cleaning and care

## no.2 Rubber surfacing (smooth or with slight profile structure)



### basic cleaning

object \_\_\_\_\_

date \_\_\_\_\_





































address \_\_\_\_\_

customer \_\_\_\_\_

work process: select one work stage from each number

room classification \_\_\_\_\_

representative \_\_\_\_\_

|                                     | cleaning method   | frequency   | * recommendations chemical products                | dosage                                  | * recommendations pad / brush / mop / cloth   | recommendations machine / tool                                      | comments  |
|-------------------------------------|---|---|--|---|---|---|---|
| 1                                   |  dusting<br> damp mopping   |    |  |   | S <b>Masslinn 2000/Floorwit white</b><br>Synthetic fur  | <b>Balit Varifix/</b><br>Balit/                                     |   |
| 1                                   |  dry vacuum cleaning   |    |  |   | V <b>Dust roller nozzle</b>   | <b>Monovac /</b><br>Scuba   |   |
| 2                                   |  chewing gum removal   |    | <b>Karpfrost</b><br>Karpotek                       | <b>100%</b>                             |   |   | if needed    |
| <b>cleaning without maintenance</b> |   |   |  |   |   |   |   |
| 3                                   |  wet scrubbing and wet vacuuming   |    | G <b>Rewit 2000</b><br>C Antiwax forte<br>B Relino | <b>10 - 20%</b><br>30 - 50%<br>20 - 50% | B  <b>Pad green/</b><br>G  <b>Pad blue/</b><br>S  <b>Microsol fibre pad/</b> | <b>Monomatic LS /</b><br><b>Watertank</b><br><b>Duovac /</b>        |     |
| 3                                   |  scrubber drying indirect method   |    | G <b>Rewit 2000</b><br>G Antiwax forte<br>B Relino | <b>10 - 20%</b><br>30 - 50%<br>20 - 50% | B  <b>Pad green/</b><br>G  <b>Pad blue/</b><br>S  <b>Microsol fibre pad/</b> | <b>Duomatic / Laser</b><br>Mambo / Samba<br>Sprinter / iMatic       |    |
| 3                                   |  spray cleaning full spray  |   | B <b>Antiwax forte</b>                             | <b>30 - 50%</b>                         |  <b>Pad blue/</b><br>V  <b>Pad green/</b>   | <b>Monomatic LS /</b><br><b>Spray unit</b>                          |   |
| 4                                   | rinsing    |  | <b>pure water</b>                                  |   |  <b>Pad blue/</b><br>S  <b>Microsol fibre pad/</b>  | <b>Monomatic LS /</b><br><b>Duovac /</b><br><b>Duomatic / Laser</b> |     |

\* basic treatment / structure: B: coated / C: waxed / D: oiled / E: sealed / F: untreated / G: maintenance care product / P: polishing / S: structured / V: heavily soiled

### important:

change pad often

Use a coin or a key to do a scratch test, to check if all the protective coating has been removed.

When white abrasion occurs, carry out a full clean to remove all the protective coating

For initial cleaning after basic cleaning, see "initial cleaning".

# General instructions for cleaning and care

## no.2 Rubber surfacing (smooth or with slight profile structure)



### protective treatment

object \_\_\_\_\_

date \_\_\_\_\_





address \_\_\_\_\_

customer \_\_\_\_\_

room classification \_\_\_\_\_

representative \_\_\_\_\_

work process: select one work stage from each number

| ↓       | cleaning method   |                         | recommendations<br>chemical products dosage |                      | recommendations<br>pad / brush / mop / cloth       | recommendations<br>machine / tool | comments   |
|---------|---|-------------------------|---|----------------------|--|-----------------------------------|--|
|         |   |                         | *   |                      | *  |                                   |  |
| 1       |  | dusting<br>damp mopping |   |                      | S<br>Masslinn 2000/Floorwit white<br>Synthetic fur | Balit Varifix/<br>Balit/          |  |
| coating |   |                         |   |                      |  |                                   |  |
| 2       |  | coating                 | Mepol HM<br>Mepol H<br>Stoner               | 100%<br>100%<br>100% | Cover for Florfix                                  | Florfix/<br>Buket plast 22l       | 1 - 3 thin layers<br>  |

\* basic treatment / structure: B: coated / C: waxed / D: oiled / E: sealed / F: untreated / G: maintenance care product / P: polishing / S: structured / V: heavily soiled

### important:

if needed

Do not coat floors with PUR coating provided in the factory

before protective treatment: the floor must be perfectly stripped, thoroughly rinsed and completely dry!

Let dry protection treatment completely between the layers and before use

Process treatment of protection: see description of method

For initial cleaning with maintenance cleaner after protective treatment, see "initial cleaning".

## General instructions for cleaning and care




### no.2 Rubber surfacing (smooth or with slight profile structure)

#### Information about the flooring




Wetrot AG cannot accept any liability for damages due to improper use.  
For security information, see the safety data sheet at [www.wetrot.ch](http://www.wetrot.ch).  
Wear protection: gloves, safety goggles, work clothes  
Follow the information and remarks on the label, product data sheet and material safety data sheet.  
The product data sheet describes the product and gives information about its application, storage. See [www.wetrot.ch](http://www.wetrot.ch)  
The recommended colours of pad and brushes consist to the actual wWetrot product range  
Follow the special cleaning and care instructions of the floor manufacturer  
The cleaning and care instructions are recommendations and suggestions and apply to floorings in object quality.



**Rubber floor coverings are sensitive to strong alkalines such as soft soap and basic cleaners. Colour change: material damage!**  
**Rubber floor coverings are sensitive to certain solvents such as ketone and ester.**

Fat-soluble colorants such as shoe polish or asphalt can penetrate into rubber floor coverings: diffusion  
Mould-release agents from production (silicone or paraffin-based) must be completely removed before basic treatment.  
Paraffin-like antioxidants can migrate to the surface over time and form white clouds. These can be polished out.



Rubber floor coverings are a blend of synthetic and natural rubber, sulphur (vulcanising agent), fillers and colour pigments.

Distinguishing feature: fire assay with a glowing hot needle in an inconspicuous place: the needle penetrates only slightly, typical rubber smell, no crater formation.



Remove loose dirt before every cleaning, damp mop smooth floors and vacuum structured floors.  
Cleaning agents and surface treatments may alter the appearance and properties of a floor's surface.  
Test on an inconspicuous spot to find which product is suitable for your requirements.  
Test beforehand on an inconspicuous spot to see if the cleaning agent or surface treatment damages the floor.  
Dirt-trapping zones, incl. dirt-trapping mats (Wetrot Gardamat) in the entrance, at least 7m long, greatly reduce the amount of dirt tracked into the building.

If you have any questions, please don't hesitate to contact us.  
For training courses, contact the Wetrot Academy, tel. +41 (0)43 255 51 43 or [academy@wetrot.ch](mailto:academy@wetrot.ch).